



# Technical Data Sheet

## QUREACC®BiDD

Composition	Bismuth dimethyldithiocarbamate
CAS No.	21260-46-8
EC No.	244-299-8
Molecular Formula	C <sub>9</sub> H <sub>18</sub> BiN <sub>3</sub> S <sub>6</sub>
Molecular Weight	570

Property	Unit	Typical Value	Test Method
Appearance	-	Coarse Bright Yellow Powder	Visual
Loss on Drying, 2 h (40°C)	%	0.5 Max.	ASTM D 4571
Bismuth Content	%	35.0 - 38.0	QCD/TM/163

### Application:

QUREACC®BiDD is accelerator used along with MBTS and Sulphur for High Temperature (160°C), High Speed Vulcanization of NR and SBR Rubbers. It is primarily used in wire and cables vulcanization of NR, SBR at high temperature for short time. Eg. Continuous vulcanisation

### Packing:

Available in 25 Kg. Drum.

### Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

### Safety:

Please refer safety data sheet.

Rev.03 DT. 01.06.2020

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

### YASHO INDUSTRIES LIMITED

**REGISTERED OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai - 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:[info@yashoindustries.com](mailto:info@yashoindustries.com)

**FACTORY - UNIT II:** Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.