



Technical Data Sheet

YAPOX®CL 30/10

Composition	Hydroquinone bis(2-hydroxyethyl) ether
CAS No.	104-38-1
EC No.	203-197-3
Molecular Formula	C ₁₀ H ₁₄ O ₄
Molecular Weight	198

Property	Unit	Typical Value	Test Method
Appearance	-	Grayish white pellets	Visual
Assay	%	99.0 min.	QCD/TM/74
Melting Point	°C	104.0 min.	QCD/TM/25
Moisture content	%	0.10 max.	QCD/TM/26
Solidification time	sec.	100.0 ± 20.0	QCD/TM/109
Hydroxyl number	mg KOH/g	560.0 ± 20.0	QCD/TM/22

Application:

YAPOX®CL 30/10 is used as Crosslinking agent/as a chain extender for polyurethanes (PU).

Packing:

Available in 125 Kg. Drum.

Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

Safety:

Please refer safety data sheet.

Rev.03 DT.01.06.2020

YAPOX is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail: info@yashoindustries.com

FACTORY – UNIT II: Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.