

Technical Data Sheet

YAPOX®IDMC



Composition	Iron(III)dimethyldithiocarbamate
CAS No.	14484-64-1
EC No.	238-484-2
Molecular Formula	C ₉ H ₁₈ FeN ₃ S ₆
Molecular Weight	417

Property	Unit	Typical Value	Test Method
Appearance	-	Light reddish black or black powder	Visual
Decomposing point	°C	240.0 min.	ASTM D 1519
Heating Loss (@ 105°C)	%	0.30 max.	ASTM D 4571
Ash content	%	22.0 max.	ASTM D 4574
Sieve Residue (@ 75μ)	%	0.50 max.	ASTM D 4572

Application:

YAPOX®IDMC acts as an Intermediate.

Packing:

Available in 20 Kg. Bag.

Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

Safety:

Please refer safety data sheet.

Rev.03 DT.01.06.2020

YAPOX is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India
TEL: +91 22 62510100/FAX : +91 22 62510199 E-Mail.:info@yashoindustries.com

FACTORY - UNIT II: Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.