



# MG BMT 75

## Technical Data Sheet

Composition: 75% 1,3,4-thiadiazole-2(3H)-thione,5,5-dithiobis  
25% Elastomeric binder

Active content CAS Number: 72676-55-2

Property	Unit	Typical Value	Test Method
Appearance	granules	Yellow	Visually
Density	g/cm <sup>3</sup>	approx. 1.49	ASTM D 792
Viscosity	ML (1+4) 80°C	< 50	ASTM D 1646
Sulfur content	%	47.0 – 49.0	LECO analysis

Packaging: 30 kgs carton box

Storage: 18 months from the date of production, store in original container in cool and dry place

Safety and toxicity: Please consult Safety Data Sheet

### **YASHO INDUSTRIES LIMITED**

**REGISTERD OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:[info@yashoindustries.com](mailto:info@yashoindustries.com)

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.