



# MG DPTT 70

## Technical Data Sheet

Composition: 70% Dipentamethylene Thiuram Hexasulfide  
30% Elastomeric binder

Active content CAS Number: 971-15-3

| Property       | Unit              | Typical Value         | Test Method   |
|----------------|-------------------|-----------------------|---------------|
| Appearance     | granules          | Beige to light yellow | Visually      |
| Density        | g/cm <sup>3</sup> | approx. 1.26          | ASTM D 792    |
| Viscosity      | ML (1+4) 80°C     | < 50                  | ASTM D 1646   |
| Sulfur content | %                 | 39.0 – 41.0           | LECO analysis |

Packaging: 25 kgs carton box

Storage: 18 months from the date of production, store in original container in cool and dry place

Safety and toxicity: Please consult Safety Data Sheet

### **YASHO INDUSTRIES LIMITED**

**REGISTERD OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:[info@yashoindustries.com](mailto:info@yashoindustries.com)

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

[www.yashoindustries.com](http://www.yashoindustries.com)