



MG DTDM 80

Technical Data Sheet

Composition: 80% 4,4'-Dithiodimorpholine
20% Elastomeric binder

Active content CAS Number : 103-34-4

Property	Unit	Typical Value	Test Method
Appearance	granules	White to biege	Visually
Density	g/cm ³	approx. 1.18	ASTM D 792
Viscosity	ML (1+4) 80°C	< 50	ASTM D 1646

Packaging: 25 kgs carton box

Storage: 18 months from the date of production, store in original container in cool and dry place

Safety and toxicity: Please refer Safety Data Sheet

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:info@yashoindustries.com

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee

www.yashoindustries.com