



MG MPTD 70

Technical Data Sheet

Composition: 70% Dimethyl diphenyl thiuram disulfide
30% Elastomeric binder

Active content CAS Number: 10591-84-1

Property	Unit	Typical Value	Test Method
Appearance	granules	Off white to gray	Visually
Density	g/cm ³	approx. 1.14	ASTM D 792
Viscosity	ML (1+4) 50°C	< 60	ASTM D 1646
Sulfur content	%	23.5 – 25.5	LECO analysis

Packaging: 25 kgs carton box

Storage: 12 months from the date of production, store in original container in cool and dry place

Safety and toxicity: Please consult the Safety Data Sheet

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.: info@yashoindustries.com

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee