



# MG TMPTMA 50

## Technical Data Sheet

Composition: 50% TMPTMA  
50% Elastomeric binder

Active content CAS Number: 3290-92-4

Property	Unit	Typical Value	Test Method
Appearance	granules	White to Off white	Visually
Density	g/cm <sup>3</sup>	approx. 1.06	ASTM D 792
Viscosity	ML (1+4) 50°C	< 50	ASTM D 1646

Packaging: 25 kgs carton box

Storage: 12 months from the date of production, store in original container in cool and dry place

Safety and toxicity: Please consult the Safety Data Sheet

### **YASHO INDUSTRIES LIMITED**

**REGISTERED OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.: [info@yashoindustries.com](mailto:info@yashoindustries.com)

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee

[www.yashoindustries.com](http://www.yashoindustries.com)