



Technical Data Sheet

QUREACC[®]TETD

Composition	Tetra Ethyl Thiuram Disulfide
CAS No.	97-77-8
EC No.	202-607-8
Molecular Formula	C ₁₀ H ₂₀ N ₂ S ₄
Molecular Weight	297

Property	Unit	Typical Value	Test Method
Appearance	-	Buff to light grey powder	Visual
Assay	%	99.0 min.	ASTM D 5297
Melting point	°C	69.0 – 73.0	ASTM D 1519
Loss on drying (@ 50°C)	%	0.3 max.	ASTM D 4571
Ash content	%	0.3 max.	ASTM D 5461

Application:

QUREACC[®]TETD functions as a primary accelerator for cure systems requiring very low or no sulphur. Less blooming than TMTD. Used in low sulphur curing of EPDM etc.

Packing:

Available in 25 Kgs. Bag.

Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

Safety:

Please refer safety data sheet.

Rev.03 DT. 01.06.2020

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:info@yashoindustries.com

FACTORY – UNIT II: Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

www.yashoindustries.com