



# Technical Data Sheet

## QUREACC®TMTM

Composition	Tetra Methyl Thiuram monosulfide
CAS No.	97-74-5
EC No.	202-605-7
Molecular Formula	C <sub>6</sub> H <sub>12</sub> N <sub>2</sub> S <sub>3</sub>
Molecular Weight	208

Property	Unit	Typical Value	Test Method
Appearance	-	Yellow powder	Visual
Assay	%	98.0 min.	ASTM D 5297
Melting point	°C	104.0 - 107.0	ASTM D 1519
Loss on drying (@ 70°C)	%	0.5 max.	QCD/TM/24
Ash content	%	0.5 max.	ASTM D 4574

### Application:

QUREACC®TMTM cause very rapid and scorch safe vulcanization of natural & synthetics rubbers. Recommended in natural, SBR, butyl, nitrile and neoprene rubbers. It is commonly used as sulphur donor to get excellent after ageing properties.

### Packing:

Available in 25 Kgs. Paper Bag.

### Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

### Safety:

Please refer safety data sheet.

Rev.03 DT. 01.05.2020

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

### YASHO INDUSTRIES LIMITED

**REGISTERED OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:[info@yashoindustries.com](mailto:info@yashoindustries.com)

**FACTORY – UNIT II:** Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

[www.yashoindustries.com](http://www.yashoindustries.com)