



Composition Zinc dibutyldithiocarbamate

CAS No. 136-23-2 EC No. 205-232-8 Molecular Formula  $C_{18}H_{36}N_2S_4Zn$ 

Molecular Weight 474

Property	Unit	Typical Value	Test Method
Appearance	-/ //	White to off white powder	Visual
Assay	%	99.0 min.	QCD/TM/150
Melting point	°C	104.0 min.	ASTM D 1519
Loss on drying (@ 70°C)	%	1.0 max.	QCD/TM/24
Zinc content	%	13.5 – 15.5	ASTM D 4004

## Application:

QUREACC®ZDBC is used in Manufacture of NR/SR latex based products, NR/IR based transparent moulded products and as a secondary accelerator for the manufacture of bloom free EPDM, NR/EPDM blend, moulded and extruded rubber products.

# Packing:

Available in 200 Kg. Drum

## Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

### Safety:

Please refer safety data sheet.

Rev.03 DT. 01.05.2020

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

#### YASHO INDUSTRIES LIMITED

REGISTERED OFFICE: Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India TEL: +91 22 62510100/FAX: +91 22 62510199 E-Mail: info@yashoindustries.com

FACTORY - UNIT II: Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896