



# Technical Data Sheet

## QUREACC®ZEPC

Composition	Zinc ethyl phenyl dithiocarbamate
CAS No.	14634-93-6
EC No.	238-677-1
Molecular Formula	C <sub>18</sub> H <sub>20</sub> N <sub>2</sub> S <sub>4</sub> Zn
Molecular Weight	458

Property	Unit	Typical Value	Test Method
Appearance	-	White to pale yellow powder	Visual
Assay	%	99.0 min.	QCD/TM/150
Melting point	°C	200.0 - 215.0	ASMTM D 1519
Loss on drying (105°C)	%	0.3 max.	QCD/TM/24
Zinc content	%	13.0 - 15.0	ASTM D 4004

### Application:

QUREACC®ZEPC is a fast curing primary or secondary accelerator for natural and synthetic rubber. It can be used in vulcanizing or curing natural rubber, acrylonitrile-butadiene (NBR) and styrene-butadiene rubber (SBR). It is especially suitable for curing latex.

### Packing:

Available in 25 Kg. paper bag

### Storage stability:

Store in a cool and dry place. Stable for up to 24 months from the date of manufacturing when stored in the original packing material in a cool and dry environment.

### Safety:

Please refer safety data sheet.

Rev.03 DT. 01.05.2020

QUREACC is a registered trademark of YASHO INDUSTRIES LIMITED and/or its respective wholly owned subsidiaries

### YASHO INDUSTRIES LIMITED

**REGISTERED OFFICE:** Office No. 101/102, Peninsula Heights, C.D.Barfiwala Marg, Juhu lane, Andheri (West), Mumbai – 400058, India  
TEL : +91 22 62510100/FAX : +91 22 62510199 E-Mail.:[info@yashoindustries.com](mailto:info@yashoindustries.com)

**FACTORY – UNIT II:** Plot No. 1713, Phase III, G.I.D.C., Vapi - 396 195, Gujarat, India TEL.: +91 260 2420896 / 2423896

Although every care has been taken in the completion of the above information & recommendation they are offered in good faith without guarantee.

[www.yashoindustries.com](http://www.yashoindustries.com)